

PRODUCT DESCRIPTION

Vulkem MPU is a Green Star compliant, solvent based, single component, Class III polyurethane waterproofing membrane designed specifically for internal wet areas.

USAGE/PURPOSE

Vulkem MPU may be used to apply a seamless, monolithic waterproof membrane to a variety of substrates in areas such as:

- Showers
- Bathrooms
- Balconies
- Terraces
- Other areas which are to be tiled and protected from UV and traffic

FEATURES & BENEFITS

- Tested successfully to AS 4654.1 ensures it meets the requirements set forth by the National Construction Code of Australia.
- Containing less than 120 g/L VOC, Vulkem MPU is a great product to use on Green Star projects.
- Meets the requirements for waterproofing materials (AS 4858) used for internal wet areas as determined by AS3740 and the National Construction Code of Australia.
- Class III membrane allows for high flexibility and movement accommodation.
- Due to solvent cure, high humidity does not slow down the curing of the membrane, making it a great solution for application in the hot, humid summer months.

PACKAGING

15L Pails

COLOUR

Grey



SHELF LIFE

6 months when stored as recommended in original unopened packaging.

STORAGE

Store in a dry cool place in an upright position in original unopened packaging.

LIMITATIONS

- Not to be used as a trafficable or UV stable waterproof membrane.
- Not to be used below grade.
- Do not apply to damp or contaminated surfaces.
- The surface temperature for product application should be between 10°C - 30°C. The curing process will slow down substantially when substrate or ambient temperatures are below 10°C

Vulkem MPU

TYPICAL PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	Vulkem MPU
Drying Time @ 23°C, 50% RH	ASTM D1640	6 - 8 hours
Full Cure Time @ 23°C, 50% RH	ASTM D1640	24 hours per coat
% Solids	By Volume	89%
Bond Strength	ASTM C794	Concrete Masonry - 150 N Plywood - 180 N
Cyclic Movement	CSIRO Moving Joint Test	Pass
Elongation at Break	AS4654.1 Appendix A	363%
Heat Ageing	AS/NZS4858	1.20 MPa, 291% Elongation
Temperature Resistance	AS4654.1 Clause 2.6	Pass
Ultraviolet Resistance	AS4654.1 Table A4	N/A - Non-Exposed
Tensile Strength	AS4654.1 Table A4	1.18 MPa
Durability	AS4654.1 Table A4	Pass
Water Vapour Transmission Rate	ASTM E96	12.83 g/m ² /24hours

* Drying times will vary depending on ambient temperature and relative humidity

SUBSTRATE PREPARATION FOR CONCRETE SURFACES

1. Concrete shall be water-cured and attain a 20 MPa minimum compressive strength. Moisture content in the concrete must be lower than 4.5% as measured using a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Representative.
2. Concrete shall be free of any laitance which may inhibit sufficient adhesion. Removal of laitance can be achieved through a variety of physical abrasion methods, such as, shotblasting (preferred method) sandblasting or grinding.
3. Concrete surface shall be properly cleaned so that the surface to receive the coating, sealant or liquid-applied flashing is free of mould, paint, sealers, coatings, curing agents, loose particles, and other contamination or foreign matter that may interfere with the adhesion.
4. Shrinkage cracks in the concrete surface that are 1.6mm wide or greater shall be ground out to a minimum 6mm wide x 12mm deep and treated according to the instructions in "Detail Work" section.
5. Structural cracks regardless of width shall be ground out to a minimum 6mm wide x 12mm deep and treated according to the instructions in "Detail Work" section.
6. Spalled areas shall be cleaned free of loose contaminants prior to repair. Because jobsite conditions vary, it is recommended that you contact your local Tremco representative. Depending on the substrate and depth of the spalled areas, a TREMCrete repair product will be recommended as the best method of repair.
7. In the event of exposed reinforcing steel, it is recommended that the structural engineer of record be contacted for investigation and for best repair method.
8. Surfaces shall be made free of defects that may telegraph and show through the finished coating. Surfaces that are rough (fins, ridges, exposed aggregate, honeycombs, deep broom finish, etc.) shall be levelled and made smooth by applying a coat of sand-filled epoxy using TREMCcoat MPE.
9. All drains shall be cleaned and operative. Drains shall be recessed lower than the adjacent substrate. The surface shall be sloped to drain to provide positive drainage as per the relevant Australian Standard.

SUBSTRATE PREPARATION FOR METAL SURFACES

All surfaces shall be sand-blasted to meet the requirements in AS1627.4, class 2.5 for "Near White Metal".

JOBSITE MATERIALS

Recommended materials and their uses are as follows:

- ❑ TREMproof 200EC Primer: A low-VOC, two-part, water based epoxy primer for use on porous substrates, such as wood and concrete to provide a vapour retarder. Also can be used on concrete based substrates to provide an efflorescence barrier.
- ❑ Vulkem 191 QD Primer: A low-VOC compliant, one-part, interlaminar primer for use in applying a fresh coat of Vulkem coating or sealant after preceding coat has been exposed to rain or for periods of time greater than 24 hours.
- ❑ TREMprime Non-Porous Primer: A low-VOC primer for use in applying urethanes to non-porous substrates such as metal, PVC and glass.
- ❑ Dymonic 100: A one-part, exceptional movement (+100/-50%) moisture-curing, gun grade polyurethane sealant for use in precast, masonry, expansion joints, control joints and for use in forming cant/fillet bead.
- ❑ TREMflex 50: A one-part, high movement (+/-50%) moisture-curing, gun grade polyurethane sealant for use in precast, masonry, control joints and for use in forming cant/fillet bead.

USAGE

The following is a guide to estimate material usage:

Coverage Rate		Thickness	
0.67m ² /L	10m ² /Pail	1.5 mm WFT	1.35 mm DFT

* All coverage rates are approximate & vary with substrate condition.

PRIMING

Note: Do not apply primers, sealant or membranes to a frosty, damp or wet surface or when substrate temperature is below 4°C or the surface temperature is above 43°C. Cure times as stated below are based upon standard ambient conditions of 23°C, 50% RH. A decrease in ambient temperature and humidity will significantly lengthen the cure time.

1. Vulkem MPU requires a Tremco approved primer on all porous substrates such as concrete, masonry, brick or stone prior to application of the Vulkem MPU membrane. TREMproof 200EC primer, or Vulkem 171 primer should be used depending on site conditions and requirements of the project. Please refer to appropriate product data sheet regarding application instructions.
2. Vulkem MPU requires TREMprime Non-Porous Primer on metal and PVC surfaces, such as puddle flanges or flashing. Please refer to appropriate product data sheet regarding application instructions.

DETAIL WORK

- ❑ Shrinkage cracks in the concrete <1.6mm wide nominally can be detailed with a 150mm wide x 1mm WFT strip of Vulkem MPU.
- ❑ Shrinkage and non-structural cracks >1.6mm wide must be appropriately prepared and filled prior to application of the Vulkem MPU membrane.
 - Grind out cracks to a minimal 6mm wide x 12mm deep.
 - Remove all loose debris and concrete dust that may inhibit adhesion.
 - Apply closed cell polyethylene backer rod or bond breaker tape into joint to prevent 3 sided adhesion of the sealant.
 - Install appropriate Tremco polyurethane sealant, TREMflex 50 or Dymonic 100 into the crack in the correct depth to width ratio.
 - Apply a 150mm wide x 1mm WFT strip of Vulkem MPU un-reinforced.
- ❑ When tiling over joints, Tremco highly encourages that the joint is expressed through to the surface of the tiles. Between the tiles, fill the joint with the appropriate Tremco joint sealant. Depending on the tile composition, polyurethane or silicone sealant may be recommend. Contact Tremco for further assistance.
- ❑ Consult Tremco for advice on the treatment of movement/expansion joints.

METHOD OF APPLICATION

1. Minimum application requirements set forth by the NCC and relevant standard (AS 3740 & AS 4654.2) should be followed, as well as project specific detail requirements/recommendations by Tremco.
2. Using a medium-nap (9mm to 13mm) roller cover, apply Vulkem MPU at the following rates to the entire area to be coated, including over applications of Vulkem MPU detail coats, but excluding expansion joints.

Application Coat	Coverage Rate	Thickness	
Waterproof Coat 1	1.33m ² /L	0.75mm WFT	0.68mm DFT
Waterproof Coat 2	1.33m ² /L	0.75mm WFT	0.68mm DFT

- Allow Vulkem MPU to cure a minimum of 6-8 hrs between coats to reduce the risk of solvent entrapment between coats. Cure rates depend on temperature and humidity. Refer to cure rate guidelines in chart at the end of this document. If the Vulkem MPU has been applied for 24 hr or longer during the ideal temperature application range (see chart on last page of document), it should be cleaned with a damp cloth of Tremco Xylol (do not saturate it). Prime coat it with Vulkem 191QD Primer. We highly recommend that you contact your local Tremco Representative with any questions on the appropriateness of priming.

CLEAN UP

- Clean all adjacent areas to remove any stains or spills with Tremco Xylol.
- Clean tools or equipment with Tremco Xylol before materials cure.
- Clean hands by soaking in hot, soapy water, then brushing with a stiff-bristle brush.

TROUBLESHOOTING

This section describes common industry application issues when certain environmental conditions exist and their remedies. If any of these should occur, it is always recommended that you contact your local Tremco Representative

- When a deck contains too much moisture, the moisture may change into a vapour, which then condenses at the concrete-membrane interface before the coating has cured and may cause blisters or bubbles, ultimately interfering with proper adhesion. If this should occur, the blisters can be cut out, allowing moisture to escape. After moisture has escaped and the surface is dry, the area can be repaired.
- If the coating application has been installed at a thickness that is greater than our installation instructions, dry times could be extended significantly. As a result, Tremco recommends that the material is applied in accordance with the installation instructions.
- If the coating is applied in very hot ambient temperatures, the air in the small spaces between the concrete particles increases in volume and forms blisters. Contact Tremco should this occur.
- If the previous coating application has not fully cured, water may become trapped between the coats and lead to large blisters. When cut out, they may still be tacky on the underside. Blisters may be cut out and repaired after the surface has been allowed to fully dry. Also, additional application will dramatically reduce the rate the material cures and full cure will take dramatically longer than normal.

WEATHER IMPACT ON COATING APPLICATION

This section discusses the impact of applying these coatings outside the ideal temperature application range of 18 to 30°C at 50% RH.

- At temperatures lower than the ideal range, the material will become viscous and it will cure at a slower rate. Refer to the chart below for approximate cure rates at varying temperatures.
- Storing materials at cooler or warmer temperatures than ideal, will affect the handling and curing characteristics of the materials.
- Substrate temperatures may affect cure rates even when ambient temperatures are high.
- Enclosed areas may slow the cure rate of the coating because air flow tends to be minimal in these areas.
- On high temperature substrates, or when the membrane is in direct sunlight, the Vulkem MPU may blister as a result

of vapour drive. For these applications, Tremco highly encourages using TREMproof 200EC primer as a vapour retarding primer to reduce the probability of these blisters occurring.

APPROXIMATE CURE TIMES IN HOURS AT 50% RH

The following is a guide to estimate cure time:

Temperature at 50% RH	Vulkem MPU
4.4 - 12.8°C	24 to 96 hours
12.8 - 18.3°C	6 to 24 hours
18.3 - 29.4°C	4 to 6 hours
29.4°C	< or = 4 hours

Variations in temperature and humidity can affect the cure rate of the coating. The above chart should be used as a guide only to determine the approximate rate of cure. Other factors can also influence the cure rate such as substrate temperature and enclosed environments. For more information about proper application procedures please contact Tremco.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

TREMCO products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with TREMCO written instructions and (b) in any application recommended by TREMCO, but which is proved to be defective, will be replaced free of charge.

Any information provided by TREMCO in this document in relation to TREMCO's goods or their use is given in good faith and is believed by TREMCO to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. TREMCO makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.